

# TECASON P

---

Chemical Designation:	Polyphenylenesulphone
DIN Abbreviation:	PPSU
Colour, Filler:	Yellowish brown, translucent

---

TECASON P is an amorphous translucent engineering plastic with higher toughness and good thermal mechanical strength for highly demanding applications.

- Main characteristics:
- Translucent
  - Tough
  - Good thermal mechanical strength
  - Good chemical and hydrolysis resistance, even to steam (sterilization)
  - Not sensitive to stress cracking
  - Dimensionally accurate
  - Good electrical insulation
  - Easily machined
  - Good weldability
  - Gamma ray resistant
  - Flame retardant UL 94 V-0

Preferred fields: Food and medical technology, electrical engineering, electronics, mechanical and automotive engineering, vacuum technology, chemical engineering, pump and instrumentation manufacture, precision engineering, jig construction, laboratory equipment, construction.

- Applications:
- Surgical instruments
  - Catalyst supports
  - Coil formers
  - Insulators
  - Sensor housings
  - Sterilization tanks
  - Flanges
  - Switch parts
  - Valve bodies
  - Sight glasses

---

Ensinger Ltd  
Wilfried Way  
Tonyrefail  
Mid Glam CF39 8JQ

Tel: 01443 678400  
Fax: 01443 675777  
Web: [www.ensinger.ltd.uk](http://www.ensinger.ltd.uk)  
Email: [sales@ensinger.ltd.uk](mailto:sales@ensinger.ltd.uk)

# TECASON P

The following information corresponds with our current knowledge and indicates our products and possible applications. We cannot give a legally binding guarantee of certain properties or the suitability for a specific application. Existing commercial patents must be observed. A definitive quality guarantee is given in our general conditions of sales. Unless otherwise stated, these values represent averages taken from injection moulding samples. We reserve the right of technical alterations.

Properties	Unit	Test method DIN EN ISO / ASTM	
<b>Mechanical</b>			
Density	g/cm <sup>3</sup>	527 / D 792	1.29
Tensile strength at yield	MPa	527 / D 638	70
Tensile strength at break	MPa	527 / D 638	
Elongation at break	%	527 / D 638	>50
Modulus of elasticity in tension	MPa	527 / D 638	2350
Modulus of elasticity in flexure	MPa	178 / D 790	2600
Ball indentation hardness	MPa	2039 / 1	
Impact strength	kJ/m <sup>2</sup>	179 / D 256	
Creep rupture strength after 1000 hrs with static load	MPa		
Time yield limit for 1% elongation after 1000 hrs.	MPa		
Coefficient of friction against hardened and ground steel p = 0,05 N/mm <sup>2</sup> , v = 0,6 m/s	-		
Wear conditions as above	µm/km		
<b>Thermal</b>			
Crystalline melting point	°C	DIN 53 736	
Glass transition temperature	°C	DIN 53 736	220
Heat distortion temperature Method A Method B	°C °C	R 75 R 75	207 214

Properties	Unit	Test method DIN EN ISO / ASTM	
<b>Thermal</b>			
Max. service temperature short term long term	°C °C		190 170
Coefficient of thermal conductivity	W/(m · K)		0.35
Specific heat	J/(g · K)		
Coefficient of thermal expansion	10 <sup>-5</sup> /K	DIN 53 483 / D 696	5.6
<b>Electrical</b>			
Dielectric constant at 10 <sup>5</sup> Hz		DIN 53 483	3.45
Dielectric loss factor at 10 <sup>5</sup> Hz		DIN 53 483	
Specific volume resistance	Ω · cm	DIN 60093	10 <sup>15</sup>
Surface resistance	Ω	DIN 60093	10 <sup>13</sup>
Dielectric strength 1 mm	kV/mm	ASTM 149	15
Tracking resistance		53 480	
<b>Miscellaneous</b>			
Moisture absorption: Equilibrium in standard atmosphere (23 °C / 50 % relative humidity)	%	62	0.37
Water absorption at saturation at 23 °C	%	62	1.1
Resistance to hot water, washing soda			resistant
Flammability according to UL standard 94			V0
Resistance to weathering			not resistant

## ENSINGER: Production and stock programme

- Semi-finished product, finished parts, injection moulded parts and profiles in more than 500 materials and modifications.
- Engineering plastics: PA extruded or cast, POM, PC, PET, PBT, PPE, PP, PE
- High temperature plastics: PI, TPI, PEEK, PPS, PES, PPSU, PEI, PSU, PVDF, PCTFE, PTFE
- Stock length: Standard 3 metres. Cast rod and sheet 2 mts. Tube up to 3,5 mts. PE, PP, PVC, and PTFE 2 mts
- Pressed/sintered semi-finished product: PI, PEEK, PPS, PTFE/PI and modifications, as well as PCTFE in special sizes ie, large discs, tubes and rings with diameters up to about 1400 mm
- Material modifications: eg glass, carbon and aramid fibre, talc, MoS<sub>2</sub>, graphite, PTFE, PE, silicone oil, internal lubrication