

## TECANAT GF 30

---

Chemical Designation:	Polycarbonate
DIN Abbreviation:	PC
Colour, Filler:	Slightly translucent 30 % glass fibre

---

TECANAT GF 30 is a 30% glass filled amorphous engineering thermoplastic with high stiffness for varied applications

- Main characteristics:
- Strong and rigid
  - Dimensionally stable
  - Wear resistant
  - Good electrical insulation
  - Easily bonded and welded
  - Good heat deflection temperature
  - Easily machined, however, care required with coolant
  - Susceptible to stress cracking

Preferred fields: Mechanical engineering, automotive engineering, textile, packaging and paper processing machinery, electronic engineering, precision engineering, electrical tools

- Applications:
- Machine parts
  - Insulators
  - Sockets
  - Housing parts
  - Plugs
  - Support rings

---

Ensinger Ltd  
Wilfried Way  
Tonyrefail  
Mid Glam CF39 8JQ

Tel: 01443 678400  
Fax: 01443 675777  
Web: [www.ensinger.ltd.uk](http://www.ensinger.ltd.uk)  
Email: [sales@ensinger.ltd.uk](mailto:sales@ensinger.ltd.uk)

## TECANAT GF 30

The following information corresponds with our current knowledge and indicates our products and possible applications. We cannot give a legally binding guarantee of certain properties or the suitability for a specific application. Existing commercial patents must be observed. A definitive quality guarantee is given in our general conditions of sales. Unless otherwise stated, these values represent averages taken from injection moulding samples. We reserve the right of technical alterations.

Properties	Unit	Test method DIN EN ISO / ASTM	
<b>Mechanical</b>			
Density	g/cm <sup>3</sup>	527 / D 792	1.43
Tensile strength at yield	MPa	527 / D 638	
Tensile strength at break	MPa	527 / D 638	130
Elongation at break	%	527 / D 638	2.5
Modulus of elasticity in tension	MPa	527 / D 638	7500
Modulus of elasticity in flexure	MPa	178 / D 790	
Ball indentation hardness	MPa	2039 / 1	148
Impact strength	kJ/m <sup>2</sup>	179 / D 256	55
Creep rupture strength after 1000 hrs with static load	MPa		>50
Time yield limit for 1% elongation after 1000 hrs.	MPa		
Coefficient of friction against hardened and ground steel p = 0,05 N/mm <sup>2</sup> , v = 0,6 m/s	-		
Wear conditions as above	µm/km		
<b>Thermal</b>			
Crystalline melting point	°C	DIN 53 736	
Glass transition temperature	°C	DIN 53 736	148
Heat distortion temperature Method A Method B	°C °C	R 75 R 75	142

Properties	Unit	Test method DIN EN ISO / ASTM	
<b>Thermal</b>			
Max. service temperature short term long term	°C °C		140 120
Coefficient of thermal conductivity	W/(m · K)		0.26
Specific heat	J/(g · K)		
Coefficient of thermal expansion	10 <sup>-5</sup> /K	DIN 53 483 / D 696	3
<b>Electrical</b>			
Dielectric constant at 10 <sup>5</sup> Hz		DIN 53 483	3.3
Dielectric loss factor at 10 <sup>5</sup> Hz		DIN 53 483	0.009
Specific volume resistance	Ω · cm	DIN 60093	10 <sup>16</sup>
Surface resistance	Ω	DIN 60093	10 <sup>14</sup>
Dielectric strength 1 mm	kV/mm	ASTM 149	30
Tracking resistance		53 480	KB 160
<b>Miscellaneous</b>			
Moisture absorption: Equilibrium in standard atmosphere (23 °C / 50 % relative humidity)	%	62	0.1
Water absorption at saturation at 23 °C	%	62	0.28
Resistance to hot water, washing soda			Not resistant
Flammability according to UL standard 94			HB
Resistance to weathering			Not resistant

### ENSINGER: Production and stock programme

- Semi-finished product, finished parts, injection moulded parts and profiles in more than 500 materials and modifications.
- Engineering plastics: PA extruded or cast, POM, PC, PET, PBT, PPE, PP, PE
- High temperature plastics: PI, TPI, PEEK, PPS, PES, PPSU, PEI, PSU, PVDF, PCTFE, PTFE
- Stock length: Standard 3 metres. Cast rod and sheet 2 mts. Tube up to 3.5 mts. PE, PP, PVC, and PTFE 2 mts
- Pressed/sintered semi-finished product: PI, PEEK, PPS, PTFE/PI and modifications, as well as PCTFE in special sizes ie, large discs, tubes and rings with diameters up to about 1400 mm
- Material modifications: eg. glass, carbon and aramid fibre, talc, MoS<sub>2</sub>, graphite, PTFE, PE, silicone oil, internal lubrication