

Carp Brand TUFNOL

Cotton fabric based laminate

- Resin:** Phenolic resin.
- Reinforcement:** Cotton fabric (fine weave)
- Description:** A top quality grade for mechanical and electromechanical applications. Made from a premium quality fine weave cotton fabric which has been specially treated to enhance the machineability and other properties. Strong, good wear resistance. Excellent machining qualities. Low water absorption with good dimensional stability. Very good electrical properties for this class of material. Resistance to high impact is slightly less than the coarser weave grades.
- Typical uses:** Used for a wide variety of components where premium quality is required. It is often chosen for components with intricate features and where accuracy and a fine machined finish is needed. Typical components include fine toothed gears, cams, geneva wheels, seal retaining rings, actuating arms, insulating sleeves and bushes, components for use at cryogenic temperatures, insulation for low and medium voltages and a wide range of other precision machined parts.
- Types available:** Natural colour is available in all sections. Graphite impregnated is available in all sections and black is available in sheet only, both subject to minimum order quantities.

SHAPES AND SIZES

Sheet

Thickness: 0.4 to 88.9mm (1/64" to 3 1/2")
Sheet Sizes: 1220 x 1220mm approx.
 1600 x 1220mm approx.
 For guaranteed minimum sheet sizes, refer to TUFNOL Ltd. For 1600 mm long sheets, minimum order quantities may apply.

Round Rod

Diameter: 3.2 to 152.4mm (1/8" to 6")
Lengths approx: 1200mm for dia. 3.2 to 120.6mm
 584mm for dia. 104.8 to 152.4mm

Round Tube

Inside diameter: 3.2 to 203.2mm (1/8" to 8")
Outside diameter: 6.3 to 228.6mm (1/4" to 9")
 Wall thickness must be less than inside diameter.
Length approx 584 for o.d. up to 15.1mm
 1200 for o.d. 9.5 to 120.6
 584 for o.d. 101.6 to 228.6

Rectangular Bar

Sizes 4.8 x 4.8mm to 76.2 x 88.9mm
 (3/16" x 3/16" to 3" x 3 1/2")
Length approx: 1200mm

Rectangular Tube

Internal size: 4.8 x 4.8mm to 69.8 x 69.8mm
 (3/16" x 3/16" to 2 3/4" x 2 3/4")
Lengths approx: 584mm for size 9.5 x 9.5 or smaller
 1200mm for sizes larger

Channel

Cut from rectangular tube. Deduct 3.2mm from relevant internal dimension to allow for tool cut.

Angle

Outside size: 6.3 x 9.5mm to 149.2 x 149.2mm
 (1/4" x 3/8" to 5 7/8" x 5 7/8")
Wall thickness 1.6 to 9.5mm (1/16" to 3/8")
Length approx 1200mm

Hexagon Bar

Across flats : 0.445" to 1.100"
 (11.3 to 28.0mm)
 The across flats dimensions are machined to suit Metric, Whitworth or other standard hexagon sizes.
Length approx: 1200mm

Carp Brand TUFNOL

SPECIFICATIONS

BRITISH STANDARDS

Sheet	BS2572 Type F1
Round Rod	BS6128 Part 2 Type PF CC 21 & 22
Rectangular Bar	BS6128 Part 4 Type PF CC 41 & 42
Hexagon Bar	BS6128 Part 6 Type PF CC 61 & 62
Round Tube	BS6128 Part 9 Type PF CC 91
Rectangular Tube	BS6128 Part 13 Type PF CC 131

NEMA *

Sheet	Nema LI-1-1983 Type LE
-------	------------------------

MIL *

Sheet	MIL-I-24768
-------	-------------

DIN *

Round Rod and Tube	DIN 7735 TYPE Hgw 2088 & 2089
--------------------	-------------------------------

*Certification to these standards is subject to special enquiry. Standard quality testing is to British Standards.

APPROXIMATE WEIGHTS

Sheets

Sheet size 1220 x 1220 approx.
Approx. weight in kg = 2.10 x thickness in mm

Sheet size 1600 x 1220 approx.
Approx. weight in kg = 2.76 x thickness in mm

Due to slight variations in density and nominal dimensions, weight cannot be calculated precisely.

Weight Formulae

Cut pieces:

Weight in kg = $\frac{1.40 \times \text{Length} \times \text{Width} \times \text{Thickness}}{1,000,000}$ (all in mm)

Rod

Weight in kg = $\frac{1.07 \times \text{Dia}^2 \times \text{Length}}{1,000,000}$ (all in mm)

Tube

Weight in kg = $\frac{1.07 \times (\text{o.d.}^2 - \text{i.d.}^2) \times \text{Length}}{1,000,000}$ (all in mm)

PHYSICAL PROPERTIES OF CARP BRAND

SHEET

PROPERTY	TYPICAL RESULT	UNITS
Cross breaking strength	150	MPa
Impact strength, notched, Charpy	8.6	kJ/m ²
Compressive strength, flatwise	350	MPa
Compressive strength, edgewise	200	MPa
Resistance to flatwise compression	1.4	%
Shear strength, flatwise	105	MPa
Water Absorption		
1.6mm thk.	55	mg
3mm thk.	70	mg
6mm thk.	90	mg
12mm thk.	125	mg
Electric strength, flatwise in oil at 90° C		
1.6mm thk.	7.2	MV/m
3mm thk.	4.9	MV/m
6mm thk.	4.0	MV/m
Electric strength, edgewise in oil at 90°C	23	kV
Insulation resistance after immersion in water	7x10 ⁹	ohms
Relative density	1.36	-
Maximum working temperature**		
continuous	120	°C
intermittent	130	°C
Thermal classification	Class E	-
Thermal conductivity through laminae	0.37	W/(mK)
Thermal expansion in plane of laminae	1.9	x10 ⁻⁵ /K
Specific heat	1.5	kJ/(kgK)

Test methods as BS2572, where applicable.

ROUND TUBES

PROPERTY	TYPICAL RESULT	UNITS
Axial compressive strength	180	MPa
Cohesion between layers	140	MPa
Water absorption	2.4	mg/cm ²
Insulation resistance after immersion in water	5x10 ⁸	ohms
Relative density	1.35	-

Test methods as BS 6128.

ROUND RODS

PROPERTY	TYPICAL RESULT	UNITS
Flexural strength	170	MPa
Water absorption	2.5	mg/cm ²
Insulation resistance after immersion in water	5x10 ⁸	ohms
Axial electric strength in oil at 90°C	15	kV
Relative density	1.35	-

Test methods as BS 6128.

**Users of highly stressed components at temperatures approaching the maximum are recommended to seek further advice from TUFNOL Ltd.

The information in this leaflet is believed to be correct, but completeness and accuracy are not guaranteed. The user shall be fully responsible for determining the suitability of products for the intended use. TUFNOL is a Registered Trade Mark.

TUFNOL Limited, P.O. Box 376, Perry Barr, Birmingham B42 2TB, England.

A full machining service is available for this and many other engineering plastics and composites.

BIRMINGHAM

Tel: 0121-356 9351
Fax: 0121-331 4235

EAST KILBRIDE

Tel: 013 552 33876
Fax: 013 552 64573

BS 5750 Part 2
(ISO 9002)
Reg. No. Q5697